

ECOZEN[®] T90H



Product description

ECOZEN[®] is a glycol-modified polyethylene terephthalate (PETG) with exceptional transparency and chemical resistance. Due to plant-derived biomass components (Carbon-based 2%), ECOZEN[®] has more heat resistance compared to SKYGREEN[®] grades. ECOZEN[®] does not contain Bisphenol derivatives (BPA, etc.) and Phthalate-based plasticizer components regulated by the EU RoHS regulations. It also meets the requirements for food contact materials in Korea, the US, Europe, China, and Japan.

Applications

- Consumer Housewares
- Home Appliance
- Food and Beverage Packaging

Key Attributes

- High Heat Resistance
- Clarity

Notes

The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.

Typical properties for

ECOZEN[®] T90H

ASTM Method

Product Information

Property	Test Method	Unit	Result
Specific Gravity	ASTM D792	-	1.23
Mold Shrinkage	ASTM D955	%	0.2 ~ 0.5
Rockwell Hardness	ASTM D785	R-scale	105
Tensile Strength @ Yield	ASTM D638	Kgf/cm ²	430
Tensile Strength @ Break	ASTM D638	Kgf/cm ²	450
Elongation @ Yield	ASTM D638	%	5.3
Elongation @ Break	ASTM D638	%	320
Flexural Strength	ASTM D790	Kgf/cm ²	690
Flexural Modulus	ASTM D790	Kgf/cm ²	18,000
Izod Impact Strength Notched @ 23 °C	ASTM D256	J/m	860
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa	ASTM D648	°C	76 / 66
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	90

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic
of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652

Typical properties for

ECOZEN[®] T90H

ISO Method

Product Information

Property	Test Method	Unit	Result
Specific Gravity	ISO 1183	-	1.23
Mold Shrinkage	D955	%	0.2 ~ 0.5
Rockwell Hardness	ISO 2039-2	R-scale	115
Tensile Strength @ Yield	ISO 527	MPa	43
Tensile Strength @ Break	ISO 527	MPa	52
Elongation @ Yield	ISO 527	%	4.5
Elongation @ Break	ISO 527	%	240
Flexural Strength	ISO 178	MPa	62
Flexural Modulus	ISO 178	MPa	1,700
Izod Impact Strength Notched @ 23 °C	ISO 180	KJ/m ²	93
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa	ISO 75	°C	78 / 66
Haze	D1003	%	< 1.0
Transmittance	D1003	%	90

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic
of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652