

# BE0350

## Description

High parison stability and good processing properties

## Application

lightweight container, Jerrican(~30ℓ)

Properties	Method	Condition	Unit	BE0350
<b>Physical</b>				
MFI(5kg)	ASTM D1238	190°C, 5kg load	g/10min	1.1
Density	ASTM D792	Method A	g/cm <sup>3</sup>	0.958
<b>Mechanical</b>				
Tensile Strength at Yield Point(MPa)	ASTM D638	50mm/min	MPa	30
Elongation at Break Point	ASTM D638	50mm/min	%	>500
Flexural Modulus(MPa)	ASTM D790	Press sheet, 1% Secant	MPa	1200
Izod Impact Strength(J/m)	ASTM D256	23°C, Notched	J/m	440
Hardeness(Shore D)	ASTM D2240	Shore D		64
ESCR	ASTM D1693	Condition B	hr	40
<b>Thermal</b>				
Melting Temperature	LG Method	by DSC	°C	134
Vicat Softening Temperature	ASTM D1525	A50	°C	127
Heat Deflection Temperature	ASTM D648	4.6kgf/cm <sup>2</sup>	°C	76

## Note

The properties data in this table are typical values, and not guaranteed specification.  
Typical resin property values are measured on a standard compression molded specimens.

Issued Date : 2022-02-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.