

# CE2080

## Description

Good property and processability suitable for CPE of B-type

## Application

HDPE Powder used to make CPE which is mainly used in wire & cable and hose application.

Properties	Method	Condition	Unit	CE2080
<b>Physical</b>				
MFI(5kg)	ASTM D1238	190°C, 5kg load	g/10min	1.2
MFI(21.6kg)	ASTM D1238	190°C, 21.6kg load	g/10min	19
Density	ASTM D792	Method A	g/cm <sup>3</sup>	0.958
Color(Yellow Index)	ASTM D1925			≤3
Bulk Density	LG Method	Powder type	g/cm <sup>3</sup>	0.42
Particle Size(Avg.)	ASTM D1921	D50(Tyler)	μm	170
<b>Thermal</b>				
Melting Temperature	LG Method	by DSC	°C	133.5

## Note

The properties data in this table are typical values, and not guaranteed specification.

Individual measurements may deviate from these values depending on the conditions under which the test specimen was prepared.

Issued Date : 2022-02-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.