

H1500K

Description

Polypropylene homopolymer(Powder type) suitable for injection molding
High flowability combined with a good mechanical property balance

Properties	Method	Condition	Unit	H1500K
Physical				
MFI	ASTM D1238	230°C, 2.16kg load	g/10min	12
Density	ASTM D1505	Density-Gradient	g/cm ³	0.9
Mechanical				
Tensile Strength at yield point(kgf/cm ²)	ASTM D638	50mm/min	kgf/cm ²	350
Elongation at Break Point	ASTM D638	50mm/min	%	>500
Flexural Modulus(kgf/cm ²)	ASTM D790	Press sheet, 1% Secant	kgf/cm ²	15000
Izod Impact Strength(kgf-cm/cm)	ASTM D256	23°C, Notched	kgf-cm/cm	3
Rockwell Hardness(R-Scale)	ASTM D785	R-Scale		100
Thermal				
Vicat Softening Temperature	ASTM D1525	A50	°C	153
Heat Deflection Temperature	ASTM D648	4.6kgf/cm ²	°C	110

Issued Date : 2022-02-11

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.