

# LF600S

## Description

EOR(Ethylene-1-Octene copolymer)

For POP(Polyolefin Plastomer) film

Additives : Antioxidant, Slip agent

## Application

Lamination film, Packaging Films

Properties	Method	Condition	Unit	LF600S
<b>Physical</b>				
MFI	ASTM D1238	190°C, 2.16kg load	g/10min	6
Density	ASTM D1505	Density-Gradient	g/cm <sup>3</sup>	0.9
Color(Yellow Index)	LG Method			-0.8
<b>Film Properties</b>				
Tensile Strength at Break Point, MD	ASTM D882	500mm/min	kgf/cm <sup>2</sup>	28
Tensile Strength at Break Point, TD	ASTM D882	500mm/min	kgf/cm <sup>2</sup>	33
Elongation at Break Point, MD	ASTM D882	500mm/min	%	470
Elongation at Break Point, TD	ASTM D882	500mm/min	%	640
Elmendorf Tear Strength, MD	ASTM D1922	500mm/min	gf/μm	8
Elmendorf Tear Strength, TD	ASTM D1922	500mm/min	gf/μm	21
Puncture Resistance	ASTM D4833		J/cm <sup>2</sup>	15.5
Haze(50μm)	ASTM D1003	50μm	%	1
<b>Thermal</b>				
Melting Temperature	LG Method	by DSC	°C	99

## Note

The properties data in this table are typical values, and not guaranteed specification.

Typical film property values are measured on 50μm single layer cast film specimens.

Issued Date : 2022-02-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.