

Grade	UF315
Product	LLDPE

General Information

Key Features

- For blown film
- Good mechanical properties, Excellent optical properties, Good processability
- Including slip agent and anti-blocking agent

Applications

General purpose film

Item	Measuring Method	Unit	Value
Physical			
Melt Flow Index	ASTM D1238	g/10min	1.1
Density	ASTM D1505	g/cm ³	0.920
Blown Film Properties (40 μm)			
Ultimate Tensile Strength	MD	ASTM D882	kgf/cm ²
	TD		
Ultimate Elongation	MD	ASTM D882	%
	TD		
Elmendorf Tear Strength	MD	ASTM D1922	g/μm
	TD		
Dart Impact Strength			760
Haze	ASTM D1709	g	6
Gross (45°)	ASTM D1003	%	11
	ASTM D2457	%	170
			12
			72

· Processing Condition : Φ50mm LLDPE Blown Film Extruder
Temperature 180°C, Die Gap 2.2mm, BUR 2.1, FLH 32cm

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001, /TS 16949

* The last update date : 2021/10/01