



## 永嘉烯 YUNGSOX

# 1124H

均聚物 HOMOPOLYMER

### 用途 Applications

- 電器用品 Electrical appliances
- 微波食品容器 Microwave food containers
- 家庭用品 Housewares

### 特性 Characteristics

- 長期耐熱性 Long term heat resistance
- 高耐熱性 High heat resistance
- 高剛性 High stiffness
- 耐磨性優 Excellent resistance to abrasion
- 光澤性佳 Good luster

### 物性 Typical Properties

項目 Properties	單位 Unit	檢驗方法 Test Method	平均值 Typical Value
熔融指數 Melt Index	g/10min	ISO1133	20
密度 Density	g/cm <sup>3</sup>	ISO1183	0.91
熔點 Melting Point	°C	DSC	---
熱變形溫度 Heat Deflection Temperature	°C	ISO75	120
軟化點溫度 Vicat Softening Temperature	°C	ISO306	155
降伏點拉力強度 Tensile Strength at Yield	Kg/cm <sup>2</sup>	ISO527	400
斷裂點伸長率 Tensile Elongation at Break	%	ISO527	50
洛氏硬度 Rockwell Hardness	R scale	ISO2039	111
剛性係數 Flexural Modulus	Kg/cm <sup>2</sup>	ISO178	17000
IZOD 衝擊強度 IZOD Impact Strength	Kg.cm/cm notch	ISO 180	23°C -20°C 3.0 ---
收縮率 Mold Shrinkage	%	FPC Method	1.3-1.7

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

### FDA 認可 FDA Approval

永嘉烯 1124H 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 1124H resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

### UL 認證 UL Certification

永嘉烯 1124H 通過美國 UL 94HB、746B **RTI 125°C** 認證，UL 檔案編號: E216959。

Yungsox 1124H is certificated with UL 94HB, 746B **RTI 125°C**, UL file no.: E216959.

Mar 2017