

永嘉烯 YUNGSOX

3084

耐衝擊共聚物 IMPACT COPOLYMER

用途 Applications

- 汽機車配件 Automotive parts
- 電器零件 Electric appliance parts
- 電池殼 Battery case
- 辦公傢具 Furniture

特性 Characteristics

- 高剛性 High stiffness
- 高耐熱性 High heat resistance
- 中衝擊強度 Medium impact strength

物性 Typical Properties

| 項目 Properties | 單位 Unit | 檢驗方法 Test Method | 平均值 Typical Value | |
|---------------------------------------|--------------------|---------------------|----------------------|-----|
| 熔融指數 Melt Index | g/10min | ISO1133 | 8.5 | |
| 密度 Density | g/cm ³ | ISO1183 | 0.90 | |
| 熔點 Melting Point | °C | DSC | --- | |
| 熱變形溫度 Heat Deflection Temperature | °C | ISO75 | 130 | |
| 軟化點溫度 Vicat Softening Temperature | °C | ISO306 | 155 | |
| 降伏點拉力強度 Tensile Strength at Yield | Kg/cm ² | ISO527 | 290 | |
| 斷裂點伸長率 Tensile Elongation at Break | % | ISO527 | 200 | |
| 洛氏硬度 Rockwell Hardness | R scale | ISO2039 | 105 | |
| 剛性係數 Flexural Modulus | Kg/cm ² | ISO178 | 14,000 | |
| IZOD 衝擊強度 IZOD Impact Strength | Kg.cm/cm notch | ISO 180 | 23°C | 10 |
| | | | -20°C | 4.5 |
| 收縮率 Mold Shrinkage | % | FPC Method | 1.3-1.7 | |

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

FDA 認可 FDA Approval

永嘉烯 3084 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 3084 resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

UL 認證 UL Certification

永嘉烯3084通過美國UL 94HB 認證，UL 檔案編號:E216959。

Yungsox 3084 is certificated with UL 94HB, UL file no.: E216959.

Jan 2015